

HOUNSFIELD
TEST REPORT

PRODUCT CODE ...:ABC123
DATE:98/01/01
BATCH NUMBER ...:54321
OPERATOR:NAME
Test Speed.....: 12.0mm/min

60/40 Brass

	Max	Break	Ext @ Brk
	N	N	mm
1	8536.000	-0.666	11.998




HOUNSFIELD
TEST REPORT

PRODUCT CODE ...:ABC123
DATE:98/01/01
BATCH NUMBER ...:54321
OPERATOR:NAME
Test Speed.....: 12.0mm/min

Normalized
Steel

	Max N	Break N	Ext @ Brk mm
1	8536.000	-0.666	11.998
2	13901.33	-2.666	8.231
Mean	11218.67	-1.666	10.114
Median	11218.67	-1.666	10.114
Std dev	3793.863	1.414	2.663



HOUNSFIELD
TEST REPORT

PRODUCT CODE ...:ABC123
DATE:98/01/01
BATCH NUMBER ...:54321
OPERATOR:NAME
Test Speed.....: 12.0mm/min

Quenched +
Tempered
Steel

	Max N	Break N	Ext @ Brk mm
1	8536.000	-0.666	11.998
2	13901.33	-2.666	8.231
3	15585.33	-2.000	6.820
Mean	12674.22	-1.777	9.016
Median	13901.33	-2.000	8.231
Std dev	3681.389	1.018	2.676

